

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 07-122303  
(43)Date of publication of application : 12.05.1995

---

(51)Int.Cl.

H01M 10/40  
H01M 4/02  
H01M 4/62

---

(21)Application number : 05-285665

(71)Applicant : SANYO ELECTRIC CO LTD

(22)Date of filing : 20.10.1993

(72)Inventor : SUEMORI ATSUSHI  
SHOJI YOSHIHIRO  
YAMAMOTO YUJI  
NISHIO KOJI  
SAITO TOSHIHIKO


---

(54) NONAQUEOUS ELECTROLYTE SECONDARY BATTERY

(57)Abstract:

PURPOSE: To enhance cycle performance by using a specific ratio of fluorine- containing polyimide resin based on the total weight of the fluorine-containing polyimide resin and carbon powder as a binder which is dissolved in slurry for applying to a negative electrode.

CONSTITUTION: A nonaqueous electrolyte secondary battery has a negative electrode manufactured by applying slurry prepared by kneading carbon powder capable of absorbing/desorbing a cation such as a lithium ion and a binder solution obtained by dissolving a binder in an organic solvent to a current collector, then by drying and solidifying. As the binder, 0.5-5wt.% fluorine- containing polyimide resin based on the total weight of the fluorine-containing polyimide resin and the carbon powder is used. The fluorine-containing polyimide resin preferably contains a fluorine-containing polyimide bond represented by the formula.



---

LEGAL STATUS

[Date of request for examination]

22.12.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

BEST AVAILABLE COPY

[Patent number] 3213458  
[Date of registration] 19.07.2001  
[Number of appeal against examiner's decision of rejection]  
[Date of requesting appeal against examiner's decision of rejection]  
[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

BEST AVAILABLE COPY